



Firwin Hard Coat Insulation



DESCRIPTION:

Firwin Hard Coat Insulation consists of a high alumina, ceramic fiber insulation surrounded by a rugged, high heat resistant composite outer surface.

ADVANTAGES:

Black color; Water and Oil resistant – prevents fluids from seeping into insulation; Non-flammable – outer surface creates a char when exposed to flame which keeps flame from penetrating substructures; Hard rugged exterior.

APPLICATIONS:

Engine compartment components requiring long term exposure to high temperatures.

Property Data for Firwin Hard Coat Insulation

Continuous use limit, °F (°C)	1" insulation	1800°F (982°C)
	½" insulation	1300°F (704°C)
Flammability		Self Extinguishing per FAR part 25.853
Thermal Conductivity BTU•in/hr•ft²•°F (w/m•k)	@ 500°F (260°C)	0.48 (0.07)
	@ 1000°F (538°C)	0.72 (0.10)
	@ 1500°F (816°C)	1.03 (0.15)
	@ 2000°F (1093°C)	1.52 (0.22)



Mechanical Data

Property	Laminate Properties	
	30 PSI (0.20 MPa) cure with postcure	Method
Ultimate Tensile Strength		
Warp-RT	47,000 PSI (324 MPa)	ASTM D638, Type 1
Fill-RT	42,000 PSI (290 MPa)	ASTM D638, Type 1
Ultimate Flexural Strength		
Warp-RT	78,000 PSI (538 MPa)	ASTM D790
Fill-RT	69,000 PSI (476 MPa)	ASTM D790
Flexural Modulus		
Warp-RT	2.6 MSI (18 GPa)	ASTM D790
Fill-RT	2.6 MSI (18 GPa)	ASTM D790
Short Beam Shear Strength		
Warp-RT	6,670 PSI (46 MPa)	ASTM D2344

DATA SHEET # HC001 REV: 0 DATE: 25/02/10

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.